

All colors represented on these charts are actual photographs of integrally colored concrete samples using Direct Colors pigments. Differences in type and even brand of cement can and will influence the final color appearance. For best results, conduct a sample pour using the exact components involved in the actual pour.

These samples are based on pounds of pigment per 94 lbs. of cement.



The samples on these two inner pages are poured with gray Portland cement. The samples on the back flap with white.



Overlay colors are achieved using one color unit premeasured by Direct Colors, and is available in all of these colors. Call with questions!

www.directcolors.com

405-275-6657

Direct Colors premium iron oxide pigments are lightfast, alkali and weather resistant. Our pigments comply with ASTM C979 when used according to ASTM's specifications. MIXING: For optimal results, we recommend using the same brand of cement, aggregates, and sand until the completion of the project, as well as the same cement to pigment ratio. Natural ingredients can and will effect the final color. Difference in slump may produce a noticeable difference in color between batches. In instances where exact color match is required, we highly recommend a test pour using the exact ingredients and ratios that will be achieved on the site. Do not use calcium chloride as a set accelerator; this has been known to cause undesired discoloration. The maximum level of pigment to cement is 10% by weight, and using less than 1% can cause a washed out appearance. Our charts and codes are based on pounds of pigment per 94 lbs. of cement material, including Portland cement, silica fume, fly ash, lime. Sand and aggregates are NOT used in this ratio. DISCLAIMER: Because the conditions of use and application of our products are beyond the control of Direct Colors Inc., Direct Colors makes no warranty regarding workmanship and other variables that do not involve the performance of our pigments. Buyer's sole remedy shall be the purchase price paid by the user or buyer for the quantity of the Direct Colors product involved.